

PART NO.	★ SIZE	COLOR	PRICES EACH		VISCOSITY		GAP	TORQUE † IN LBS.		CURE SPEEDS @ 75°F		TEMPERATURE
			1-4	5+	сP	THIXOTROPIC	FILL	BREAKING	PREVAILING	FIXTURE	FULL	RANGE
7242	50ml	Blue	\$18.00	\$17.25	1,000	YES	.007"	100	50	20 minutes	24 hours	-75°F to 300°F
7262	50ml	Red	\$18.00	\$17.25	2,500	YES	.010"	170	150	5 minutes	24 hours	-75°F to 300°F
7290	50ml	Green	\$18.00	\$17.25	15	NO	.003"	90	350	3 minutes	24 hours	-75°F to 300°F
7609	50ml	Green	\$18.00	\$17.25	160	N/A	.005"	Shear Strength PSI 3,000*		8 minutes	24 hours	-75°F to 400°F

† Torque values measured using a 3/8-16 phosphate steel nuts and bolts.

Values measured using 1/2" diameter degreased steel pins and collars per MIL-2-46082B.



ASTIC PROCESS EQUIPMENT, INC.

6385 MONTESSOURI STREET LAS VEGAS, NEVADA 89113-1186 702-433-6385 • FAX: 702-433-6388 TOLL FREE: 800-258-8877 www.ppe.com e-mail: sales@ppe.com Toll Free: USA, Canada & Mexico 800-362-0706 Order Fax: 800-223-8305